

Patent claims

1. Mixture containing

5 A) vinylcyclohexane-based polymer and

B) stabiliser system containing lactone, sterically hindered phenol and phosphite compound.


10 2. Mixture according to claim 1, containing 0.001 to 2 wt.% (based on the polymer used) of stabiliser system B.

3. Mixture according to claim 1, containing 0.005 to 1 wt.% of stabiliser system B.

15 4. Mixture according to claim 1 to 3, containing as stabiliser system the following compounds:

lactone corresponding to formula (I)

20




25

wherein

R¹, R², R³ and R⁴, independently of each other, represent hydrogen, C₁-C₆-alkyl, or a 5 or 6-membered ring alkyl,

30

sterically hindered phenol corresponding to formula (II)




wherein

R^5 and R^6 , independently of each other, represent hydrogen or C_1 - C_6 -alkyl, a 5 or 6-membered ring,

n represents an integer from 1 to 4, and

R , independently, represents hydrogen, C_1 - C_6 -alkyl, C_1 - C_6 -alkoxy, a 5 or 6-membered ring,

phosphite component corresponding to formula (III)






wherein

R^7 and R^8 , independently of each other, represents hydrogen, C_1 - C_6 -alkyl, also as a 5 or 6-membered ring or as branched alkyl, and

x and y , independently of each other, represent 0, 1, 2, 3, 4, 5, and

n represents 1 or 2, wherein if n = 1 the free valence bond of the carbon atom is attached to hydrogen, C₁-C₆-alkyl, C₁-C₆-alkoxy or to 5,6 rings.

5. Mixture according to one or more of the preceding claims, containing the following compounds:



6. Mixture according to one or more of the preceding claims, wherein the stabiliser system contains
- 5 to 95 parts by wt. (based on component B) of compound(s) corresponding to formula I
- 5 to 95 parts by wt. (based on component B) of compound(s) corresponding to formula II
- 5 to 95 parts by wt. (based on component B) of compound(s) corresponding to formula III.